



## **ANTIRUGGINE R.E. – industrial products**

Synthetic primer, antirust, fast drying, with an excellent anticorrosive and adhesive power. The super-phenolic component of its binder makes it suitable for protecting iron manufactures and industrial carpentry. For its elasticity and adhesion is also suitable as a primer for galvanized structures, properly degreased. Overpainted with our with fast drying enamel **Rapiterm** and nitrosynthetic enamels.

### **SPECIFICATIONS**

**Composition:** short oil alkyd resin, phenol linen timber.

**Nature of the pigments:** inorganic highly resistant to weathering.

**Solid content:** 72%±2.

**Recommended film thickness per coat:** 25-35 µ.

**Dried product appearance:** matt.

**Viscosity at 20 ° C:** 18-20''

**Application:** brush, roller.

**Dilution:** 5% approx. with nitro thinner.

**Yield:** 10 sqm/lt, 1 coat.

**Drying time:** to touch 30 minutes, hardened in depth 16-24 hours.

**Recoat:** 12-24 hours, under normal conditions of temperature and humidity.

### **METHOD OF USE**

Ensure that the surface is thoroughly dried and aged. If necessary, take measures to reconstruct or consolidate the surface by using specific products. Remove any deposits of dust, smog or other by brushing. Level any irregularities in the surface and treat holes, cracks, crevices and gaps.

- *Never painted iron:* Clean and degrease the surface with nitro thinner, then apply a coat of **Antiruggine R.E.** (Caf). Make sure the product is completely dry before applying the nitro thinner enamels such as **Rapiterm** (Caf).

- *Already painted iron:* brush the surface removing all traces of rust; then proceed as above.

### **CLIMATIC CONDITIONS**

To avoid compromising the optimal performance of the product, we recommend the application in specific climatic conditions:

- Apply at temperatures between +5 °C and +35 °C;
- Avoid the application on surfaces heated by strong sunlight,
- Avoid application when rain is imminent,
- Avoid application in presence of moisture;
- The painted surface must be kept away from rain and humidity for 48 hours.

### **USEFUL TIPS:**

- Store at room temperature.
- Close the container tightly after each use.
- Protect surfaces not to be painted (windows, tiles, glass etc ...).

The technical information contained in this technical sheet are based on our practical experience and laboratory testing and are purely indicative. We offer products and operating systems in perfect correspondence with the highest quality standards, provided that the instructions for use are followed in accordance with the needs and the professional knowledge of utilization. The application of the products takes place outside of our control and therefore is under the sole responsibility of the customer. Our technical department is always at your complete disposal to provide any further information or clarification.



**NUOVA CAF S.r.l.**

Via L. Einaudi, 6/7\_Z.I. - 61032 Fano (PU)\_ Italy

Tel. +39 0721 854235 - fax +39 0721 854596

[www.nuovacaf.it](http://www.nuovacaf.it) - [info@nuovacaf.it](mailto:info@nuovacaf.it)

Protect from frost.

**Packaging:** 0,500 - 2,5 - 16 lt.

**Color:** white, grey, oxide red.

**Washing tools:** use nitro thinner immediately after use.

## Specification Item

> Protect all surfaces not subject to application of paint.

> Preparation of the substrate by manual brushing or washing with high pressure washer machine, depending on the nature and intensity of the dirt.

> Application of one coat of nitro-synthetic undercoat, fast drying, with excellent anticorrosive and adhesive power **Antiruggine R.E.** (Caf) by roller or brush, making a dry thickness of at least 25-35 $\mu$  per coat.

> All applications must be performed on completely dry surfaces, with the ambient temperature and that of the surfaces to be painted between +5 °C and +35 °C with relative humidity not exceeding 80%. If you ever experience environmental conditions other than those mentioned above, as well as in the presence of wind, dust, smoke, etc ..., the application should not be initiated.