



NUOVA CAF S.r.l.

Via L. Einaudi, 6/7_Z.I. - 61032 Fano (PU)_ Italy

Tel. +39 0721 854235 - fax +39 0721 854596

www.nuovacaf.it - info@nuovacaf.it

FLATTING IMPREGNANTE FINITURA CERATA – solvent based woodstains

Transparent varnish to protect the wood inside and outside that differs from traditional breathable products for wood for these characteristics:

- satin appearance, soft, similar to a wax finish;
- high elasticity and exceptional outdoor durability, made with special resins;
- water repellency and at the same time permeability of internal humidity of the wood.

SPECIFICATIONS

Nature of the pigments: resins urethane /alkyd non-yellowing non-flaking, filter against ultraviolet radiation and free radicals

Solid content: 48%±2.

Recommended film thickness per coat: 25-30 µ.

Dried product appearance: satin, waxed effect.

Viscosity at 20 ° C: 8-10".

Application: brush, spray, roller.

Dilution: ready to use.

Yield: 14-15 sqm/lt for 1 coat, depending on the surface to be treated.

Drying time: to touch 2-3 hours, hardened in depth 18-24 hours.

Recoat: 18-24 hours under normal conditions of temperature and humidity.

METHOD OF USE

Ensure that the surface is thoroughly dried and aged. If necessary, take measures to reconstruct or consolidate the surface by using specific products. Remove any mold, efflorescence and any old peeling paint by brushing or washing. Remove any deposits of dust, smog or other by brushing. Level any irregularities in the surface and treat holes, cracks, crevices and gaps.

- *Never painted wood:* Sand lightly in order to remove any pieces of wood not well anchored; putty imperfections with stucco, if necessary. Sand repair areas and remove dust. Proceed with the application of solvent based woodstain **Impregnante (Caf)** in desired color, taking care to sand the surface between one layer and another. Apply one or two coats of **Flattig Impregnante Finitura Cerata (Caf)**, depending on the desired protection. For outdoor use it is recommended two coats of application. We do not recommend the application of **Flattig Impregnante Finitura Cerata (Caf)** on raw wood without having first applied **Impregnante (Caf)**.

- *Already painted wood:* remove the parts of old paint not well anchored by sanding and brushing; then proceed as above.

USEFUL TIPS:

- Store at room temperature.
- Close the container tightly after each use.
- Protect surfaces not to be painted (windows, tiles, glass etc ...).

The technical information contained in this technical sheet are based on our practical experience and laboratory testing and are purely indicative. We offer products and operating systems in perfect correspondence with the highest quality standards, provided that the instructions for use are followed in accordance with the needs and the professional knowledge of utilization. The application of the products takes place outside of our control and therefore is under the sole responsibility of the customer. Our technical department is always at your complete disposal to provide any further information or clarification.



CLIMATIC CONDITIONS

NUOVA CAF S.r.l.

Via L. Einaudi, 6/7_Z.I. - 61032 Fano (PU)_ Italy

Tel. +39 0721 854235 - fax +39 0721 854596

www.nuovacaf.it - info@nuovacaf.it

To avoid compromising the optimal performance of the product, we recommend the application in specific climatic conditions:

- Apply at temperatures between +5° C and +35° C;
- Avoid the application on surfaces heated by strong sunlight,
- Avoid application when rain is imminent,
- Avoid application in presence of moisture;
- The painted surface must be kept away from rain and humidity for 48 hours.

Protect from frost.

Packaging: 0,750 – 2,5 L.

Color: transparent.

Washing tools: use white spirit immediately after use.

Specification Item

> Protect all surfaces not subject to application of paint.

> Preparation of the substrate by manual brushing or washing with high pressure washer machine, depending on the nature and intensity of the dirt. If the surfaces to be treated were covered with organic paints is advisable total removal of these paintings.

> Application of two coats of solvent-based satin finishing woodstain for the protection of wood **Flatting Impregnante Finitura Cerata (Caf)**, waiting 18-24 hours between coats, after having treated the wooden surface with **Impregnante (Caf)**.

> All applications must be performed on completely dry surfaces, with the ambient temperature and that of the surfaces to be painted between +5° C and +35° C with relative humidity not exceeding 80%. If you ever experience environmental conditions other than those mentioned above, as well as in the presence of wind, dust, smoke, etc ..., the application should not be initiated.

The technical information contained in this technical sheet are based on our practical experience and laboratory testing and are purely indicative. We offer products and operating systems in perfect correspondence with the highest quality standards, provided that the instructions for use are followed in accordance with the needs and the professional knowledge of utilization. The application of the products takes place outside of our control and therefore is under the sole responsibility of the customer. Our technical department is always at your complete disposal to provide any further information or clarification.